

## **CIRCLE SYSTEMS, INC.**

479 West Lincoln  
P.O. Box 1228  
Hinckley, IL 60520  
Ph.: 815-286-3271  
Fax: 815-286-3352  
customerservice@circlesafe.com



---

### **Technical Bulletin #275** **Mi-Glow® 600LS-RTU**

Mi-Glow® 600LS-RTU is a Ready-to-Use oil bath packaged in a hand-held spray bottle. The bath contains Mi-Glow® 600 red particles and CircleSol M, a refined petroleum distillate. It is designed to be used with visible light for revealing discontinuities found in structural fabrications. Mi-Glow® 600LS-RTU can be further enhanced when used with a black light or blue light.

#### **Properties**

Particle Color: Red

Concentration: 8.0 g/l

Particle Size: Not less than 98% passage through US Standard No. 325 (45 µm). The typical range of particle sizes is from 5 to 20 µm, with an average particle size of 7 µm.

Particle Certification: Particles, carrier and mixture meet or exceed all relevant industry specifications, including but not limited to MIL-STD-1949, MIL-STD-271(SH), ASTM E 709, ASTM B & PV Code - Section V and NAVSEA 250-1500-1. AMS 3041, AMS 3042, AMS 3161, AMS 2641 and DOD-

Temperature Limits: 32-120°F (0-49°C)

Shelf Life: Five (5) years, when sealed bottles are not subjected to excessive heat or cold. A Certificate of Shelf Life is available upon request.

#### **Directions for Use**

Preparation: Thoroughly shake the bottle, insert the spray nozzle and apply to the parts for inspection.

Lighting: A minimum of 100 foot candles (1000 lux) of visible light at the part surface per ASTM E 709 and ASTM E 1444 is recommended.

Concentration Test: If it becomes necessary to verify the concentration in the bottle, thoroughly shake the bottle and the method of test should be as follows:

1. Fill a 100 ml graduated centrifuge tube as specified in Guide E709, or equivalent, to the 100 ml mark with suspension directly from the bottle. Demagnetize the suspension, if considered necessary, and let it stand undisturbed for a minimum of 60 minutes or until completely settled.
2. Read the volume of the precipitate in the graduate. The recommended volume is between 1.2 to 2.4 ml.

---

DISCLAIMER: OUR TECHNICAL ADVICE, INFORMATION AND STATEMENTS GIVEN VERBALLY, IN WRITING OR IN THE FORM OF TEST RESULTS, ARE OFFERED FOR YOUR GUIDANCE WITHOUT WARRANTY. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. IT IS THE USER'S RESPONSIBILITY TO TEST THE SUITABILITY OF EACH PRODUCT FOR HIS INTENDED PROCESS AND APPLICATIONS. OUR GUARANTEE IS LIMITED TO THE CONSISTENT QUALITY OF OUR PRODUCTS.

---