

ZL-19

Level 1 Water Washable Fluorescent Penetrant

A water-removeable Level 1 penetrant, ZL-19 is designed for use on rough or unmachined surfaces such as castings and forgings to find larger discontinuities in non-safety critical components. It is ideal for inspecting automotive and general industrial components such as engine cylinder blocks, power train components, rocker arms, pistons, steering knuckles, etc.

ZL-19 washes off parts with ease, leaving less background for clearer indications – even on rough surfaces. The quick rinsing reduces water usage in the inspection process which helps users reduce their over-all cost per part by reducing penetrant loss through drag-out, speeding up the washing and inspection process, and cutting rinse water costs.

ZL-19 can be used with ZP-4D dry powder developer, with ZP-5B water suspendible developer in an agitated tank or with ZP-9F non-aqueous developer. With a UV-A light source, indications will appear as a bright green-yellow fluorescence.

ZL-19 is listed on the QPL SAE AMS 2644 Qualified Product List.



BENEFITS

Increase indication detection on cast parts & rough surfaces

- Increase detection of defects in cast parts, such as hot tears, laps, or cold shuts
- Indications stand out more because of reduced background fluorescence, even on rough cast surfaces

Speed up your inspection process

- Quickly apply and remove penetrant due to high surface wetting and easy washability
- ZL-19 is spray-friendly and will not clog nozzles in automated lines, for less maintenance downtime

Performance value

- Use less penetrant per part, thanks to lower drag out
- Penetrant can be reused from the dwell cycle, so more of it stays in your tank instead of getting carried away on parts

Maximize operator comfort and safety

- Promotes better inspection quality by providing the operator with a more comfortable work environment
- Reduces discomfort from strong odors
- Exceeds all EHS requirements

FEATURES

- Level 1 sensitivity
- Water washable
- Excellent rough surface washability
- Bright, high contrast indications
- Clean rinsing on cast parts
- Won't clog spray nozzles in automated systems
- Good surface wetting
- High flash point
- Easy washability
- Less time to rinse
- Use less penetrant per part

APPLICATIONS

Defect location: open to surface

Ideal for:

- Castings
- Forgings
- Rough surface finish
- Unmachined parts
- Engine cylinder blocks
- Power train components
- Rocker arms
- Pistons
- Steering knuckles
- Automated penetrant lines

Defect examples:

- Cracks
- Seams
- Cold shuts
- Delamination
- Porosity
- Hot tears
- Laps

PROPERTIES

Flash Point	> 200°F / 93°C
Density	0.85 g/cc / 7.08 lb/gal
Viscosity (at 100°F / 38°C)	5.62 cs
NPE-Free	Yes

Revised: April 2022

SPECIFICATION COMPLIANCE

- AECL
- AMS 2644
- ASME
- ASTM E1417
- ASTM E165
- Boeing BAC 5423 PSD 6-46 or 8-4
- Boeing PS-21202
- MIL-STD-2132
- MIL-STD-271
- NAVSEA T9074-AS-GIB-010/271
- QPL SAE AMS 2644

USE RECOMMENDATIONS

NDT Method	Penetrant Testing, Fluorescent
Type	1
Method(s)	A / C
Sensitivity Level	1, low sensitivity
Required Equipment	UV light source
Usage Temperature	40 to 125°F / 5 to 52°C
Storage Temperature	50 to 86°F / 10 to 30°C

PACKAGING

5 gal / 18.9 L pail 01-3263-40
 55 gal / 208 L drum 01-3263-45

HEALTH AND SAFETY

Review all relevant health and safety information before using this product. For complete health and safety information, refer to the product Safety Data Sheet, which is available at www.magnaflux.com.

